

PRODUCT DATA

PRODUCT NAME: AK 315

PRODUCT DESCRIPTION: Water Based, fire Resistant compound.

PHYSICAL DATA

Color: Black / Grey

Viscosity: Thick flowing Liquid app. 30,000 Mega Pascal

Specific Gravity: 1.1

Ph Value: 7.6

Solid Contents: 70%

Odor: Odor less

Limiting Oxygen Index: Over 70

Storage Temperature: Store in shade (5-30 Degree C)

Shelf Life: One year at room temperature

Minimum Packing: 20kg

Cleaning of Surface & Thinner: Water

Drying Time:

Touch Dry: 2 hours

Hard Dry : 24 hours

Complete Curing: 7 days(at 25 degree C, 65%RH)

RESISTANCE GUIDE

Fire Resistance : 4 hours fire rating when tested as part of Cable fire barrier as per BS-476 part 8.

Acid : No effect (5 % HCl)

Alkali : No effect (5 % NaOH)

Water : No effect (40 degree C 7 days)

SURFACE PREPARATION

Remove grease, oil, coal dust and other contaminants from the opening area before sealing the cavity with AK-315.

HEALTH & SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant National Health, Safety & Environmental standards and regulations.. Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

APPLICATION METHOD

AK – 315 is available in trowel form and can directly be fills in cavity/ gaps from where fire/ smoke can escape during fire. Ensure that no gap or cavity remains during the application.

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet contact us.

NOTES

Do not apply AK-315 when temperature falls below 10°C or rises above 50°C and when Relative Humidity is above 85%, Do not apply during rain, fog or mist.

DISCLAIMER

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability for negligence which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.